

ABRASION RESISTANCE REPORT

ACCORDING TO ISO 7784 (ASTM D4060)

Date: 20-Aug-18

Name Analyst: S. Meuwese

Client: Recoat BV

Test no: 2018340071

MATERIAL:

Coating:	Recoat 2K Concrete	Mfg.	Dercom BV
Batch no:	N/A	Art no:	59261

TEST EQUIPMENT:

Type:	Taber Abraser				Model:	5135	
Wheel:	CS-10						
Parameters:	Load:	1.0 KG	Suction:	50%	RPM:	60	
Wheel Refaced:	At start:		Yes		During test:		No
End point of test:	1000 cycles						

	Wear	Weight			Conditions	
Sample	Cycles	Before	After	Loss	Temp.	Humidity
1	1000	40138.1 mg	40090.9 mg	47.2 mg	24°C (75°F)	62%RH
2	1000	39914.0 mg	39868.7 mg	45.3 mg	24°C (75°F)	62%RH

TABER WEAR FACTOR: 46.3