

ABRASION RESISTANCE REPORT

ACCORDING TO ISO 7784 (ASTM D4060)

Date: 10-Aug-20

Name Analyst: S. Meuwese

Client: Recoat BV

Test no: 2020330091

MATERIAL:

Coating:	Recoat AM Protector Spray	Mfg.	Dercom BV
Batch no:	N/A	Art no:	N/A

TEST EQUIPMENT:

Type:	Taber Abraser				Model:	5135	
Wheel:	CS-10						
Parameters:	Load:	1.0 KG	Suction:	50%	RPM:	60	
Wheel Refaced:	At start:		Yes		During test:		No
End point of test:	1000 cycles						

	Wear	Weight			Conditions	
Sample	Cycles	Before	After	Loss	Temp.	Humidity
1	1000	38563.2 mg	38511.8 mg	51.4 mg	23°C	20%RH
2	1000	38529.7 mg	38477.3 mg	52.4 mg	23°C	20%RH

TABER WEAR FACTOR: 51.9