

Test Report

Abrasion Resistance Test

Report: 2022420019
Issued by: Mr. S. Meuwese
Date: October 18, 2022

Client: Recoat B.V.
Product: art. 88142 - Recoat 2K Floor Mat 4:1

Test Method according to

ISO 7784 (ASTM D4060)

CONTENTS

1.	TEST MATERIAL	page 2
2.	TEST EQUIPMENT	page 2
3.	TEST RESULTS	page 2

Copyright notice

The information in this report is protected by the Dutch Copyright Act and all copyrights are vested in Dercom. The distribution and reproduction of the information in this report without the prior written consent of Dercom is prohibited. © 2021 Dercom.

1. TEST MATERIAL

Coating:	Recoat 2K Floor Mat 4:1	MFG:	Dercom B.V.
Batch no.:	N/A	Art. no.:	88142
Substrate:	Recoat Multi Primer	MFG:	Dercom B.V.

2. TEST EQUIPMENT

Type:	Taber Abraser				Model:	5135	
Wheel:	CS-10						
Parameters:	Load:	1.0 KG	Suction:	50 %	RPM:	60	
Wheel Refaced:	At start:		Yes	During test:	Yes, every 1000		
End point of test:	4000 cycles						

3. TEST RESULTS

Wear		Weight		Conditions	
Cycles	Before	After	Loss	Temp.	Humidity
1000	33959.3 mg	33938.5 mg	20.8 mg	22°C	58 % RH
2000	33938.5 mg	33914.8 mg	23.7 mg	22°C	58 % RH
3000	33914.8 mg	33895.5 mg	19.3 mg	22°C	58 % RH
4000	33895.5 mg	33873.7 mg	20.8 mg	22°C	58 % RH

TABER WEAR FACTOR: 21.4 mg loss per 1000 cycles.

Copyright notice

The information in this report is protected by the Dutch Copyright Act and all copyrights are vested in Dercom. The distribution and reproduction of the information in this report without the prior written consent of Dercom is prohibited. © 2021 Dercom.

Checked and approved by:



Mr. F. Derks
Laboratory R&D management

Our products are suitable for professional use only.

Registered processing times are valid under conditioned application circumstances only. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any date, weights, proportions, etc. given herein are for general information purpose only; they may change without prior information and do not constitute the quality of the products (product specification). For technical support and advice with concern to choices of coatings systems and methods of application our technical staff will be at your service at all times.

Confidentiality

This report and the information therein is strictly confidential and is exclusively intended for the recipient of this report. The recipient of this report will keep all information in it strictly confidential and will not disclose, copy, reproduce or distribute any of it or otherwise make it available to any person or third party without the specific prior written consent of Dercom. The recipient of this report undertakes with Dercom that it will use any of the information in this report for internal purposes only.

Copyright notice

The information in this report is protected by the Dutch Copyright Act and all copyrights are vested in Dercom. The distribution and reproduction of the information in this report without the prior written consent of Dercom is prohibited. © 2021 Dercom.